


FTTH DROP OPTIC FIBER CABLE

1、Introduction of fiber optical fibers

The typical bow-type drop optical cable includes central optical fibers with 2 steel wire as the strength members placed on both sides, steel as messenger wire, a LSZH sheath is extruded outside.

2、Cable Cross -Section



3、Fiber Optical

Fiber count	2
Color of fiber	Blue Orange
Fiber Type	G657A2
Strength member	Steel wire
Supporting messenger wire	1.0MM*x1 steel wire
Outer sheath	LSZH Lower smoke zero halogen frame retardant & UV Anti
Cable Diameter dimensions	2.0(Height) × 5.0W ± 0.1 mm(width)
Operation temperature range	-20 °C to + 70 °C
Installation temperature range	-20 °C to + 60 °C
Transport and storage temperature range	-20 °C to + 70 °C
Tension Load (N)	Short term :800N Long term :500N
Crush Load(N)	Long term 1000 N/100mm Short term:2200N/100mm
Minimal installation bending radius	30 x OD
Minimal operation bending radius	15 x OD
Cable marking	The marking length 1meter apart , as required



4、G657A2 fiber

Category	Description	G657A2
		Standard
Optical transmission performance	Attenuation coefficient	1310nm ≤ 0.35
		1383nm ≤ 0.35
		1550nm ≤ 0.21
		1625nm ≤ 0.23
	Attenuation inhomogeneity	1310nm、1550nm ≤ 0.05
	Attenuation discontinuity	1310nm、1550nm ≤ 0.05
	Wavelength attenuation characteristics	1288~1330nm ≤ 0.05
		1525~1575nm ≤ 0.05
	Dispersion characteristic	The zero dispersion wavelength nm 1300~1324
		Zero dispersion slope ≤ 0.092
		1288~1339nm ≤ 3.5
		1271~1360nm ≤ 5.3
		1550nm ≤ 18
		1625nm ≤ 22
	The polarization mode dispersion of the fiber	≤ 0.1
	Fiber cutoff wavelength	≤ 1260
	Macro bending loss (10 laps, 30mm)	1550nm ≤ 0.03
		1625nm ≤ 0.1
		(1 lap, 20mm) 1550nm ≤ 0.1
		(1 lap, 20mm) 1625nm ≤ 0.2
		(1 lap, 15mm) 1550nm ≤ 0.5
		(1 lap, 15mm) 1625nm ≤ 1.0
		Mode field diameter 1310nm 8.6 ± 0.4
dimension parameter	Warp degrees	≥ 4.0
	Cladding diameter	125 ± 0.7
	Core/package concentricity	≤ 0.5
	Cladding non-circularity	$\leq 1.0\%$
	Coating diameter	243 ± 5
	Coating concentricity	≤ 8
	Coating roundness	$\leq 3\%$
mechanical property	Strain	$\geq 1.05\%$
	Tensile strength(10m)	15% Weber fracture probability 2.76
		50% Weber fracture probability 3.45
	Fatigue parameters Nd	≥ 22
	Coating peak stripping force N	1.0~8.9
	Coating average stripping force N	1.0~5.0
	Environmental performance	Additional damping temperature cycle (-60°C ~ +85°C) dB/km@1310nm, 1550nm, 1625 nm ≤ 0.05
		Wet and heat aging (+85±2°C, 85%RH, 30 days) dB/km@1310nm, ≤ 0.05

1550nm, 1625 nm	
High temperature aging($85\pm2^{\circ}\text{C}$, 30 days) dB/km @1310nm, 1550 nm, 1625 nm	≤ 0.05
Additional attenuation of flooding ($23\pm2^{\circ}\text{C}$, 30 days) dB/km @1310nm, 1550 nm, 1625 nm	≤ 0.05

5、 Package

Item	Index
Length and packaging	2000m/plywood reel
Plywood reel size	360*340*360mm
Net weight	40.0kg/km
Gross weight	41.5kg/box
Packaging details	See the picture below

1)



2)



3)



-----End -----